

# Engineering Properties U.S. and Metric Equivalent

## Technical Engineering Properties

Reynobond® composite panels consist of a thermoplastic compound core faced with two sheets of aluminum. There are two varieties, a Polyethylene (PE) core and a Fire Resistant (FR) core.

PROPERTY		UNITS	RB120PE- 3mm	RB160FR - 4mm	Solid Al <sup>(1)</sup>
THICKNESS		in mm	0.118 3.0	0.157 4.0	0.197 5.0
WEIGHT		lb/ft <sup>2</sup> kg/m <sup>2</sup>	0.94 4.59	1.53 7.48	2.78 13.57
BOND IN-TEGRITY	MIN. BOND STRENGTH ASTM D1781	in-lb/in Nm/m	22.5 100	22.5 100	-
	FLATWISE SHEAR ASTM D1002	lb/in <sup>2</sup> MPa	1.297 8.94	92.8 6.4	-
ALLOWABLE BENDING STRESS		lb/in <sup>2</sup> MPa	11,500 79.3	11,500 79.3	11,500 79.3
COEFF. OF EXPANSION ASTM E228		in/in/°F mm/mm/°C	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>
STIFFNESS (EI) ASTM D393		lb-in <sup>2</sup> /in MPa-cm <sup>4</sup> /m	807 9.1x10 <sup>4</sup>	1,262 1.4x10 <sup>4</sup>	6,434 7.4x10 <sup>4</sup>
FLEXULAR MODULUS (E) ASTM C393		lb/in <sup>2</sup> MPa	8.3x10 <sup>6</sup> 5.7x10 <sup>4</sup>	6.7x10 <sup>6</sup> 4.6x10 <sup>4</sup>	10x10 <sup>6</sup> 6.9 x10 <sup>4</sup>
MOMENT OF INERTIA (I)		in <sup>4</sup> /in cm <sup>4</sup> /m	0.97x10 <sup>-4</sup> 0.159	1.89x10 <sup>-4</sup> 0.310	6.37x10 <sup>-4</sup> 1.042
SECTION MODULUS		in <sup>3</sup> /in cm <sup>3</sup> /m	1.65x10 <sup>-3</sup> 1.065	2.41x10 <sup>-3</sup> 1.555	6.47x10 <sup>-3</sup> 4.167
TENSILE YIELD		lb/in <sup>2</sup> MPa	8,300 57.23	6,367 43.90	19,000 130.0
FLATWISE TENSILE ASTM C297		lb/in <sup>2</sup> MPa	1,483 10.22	961 6.62	-
"R" THERMAL RESISTANCE		ft <sup>2</sup> hr <sup>2</sup> F/BTU m <sup>2</sup> K/w	0.034 6.0x10 <sup>-3</sup>	0.026 4.5x10 <sup>-3</sup>	-
MAXIMUM WIDTH		in mm	62 1,575	62 1,575	-
MAXIMUM LENGTH		in mm	243 6.172	243 6.172	-
FIRE PERFORMANCE <sup>(2)</sup>		ASTM E84 ASTM D635	Class A CC1	Class A CC1	-

<sup>(1)</sup> Solid aluminium properties are based on alloy 3105-H25

<sup>(2)</sup> For a complete list of Fire Tests and results, contact manufacturer

Information contained herein or related hereto is intended only for evaluation by technically skilled persons, with any use thereof to be at their independent discretion and risk. Such information is believed to be reliable, but Arconic Architectural Products LLC (AAP) shall have no responsibility or liability for results obtained or damages resulting from such use. AAP grants no license under, and shall have no responsibility or liability for infringement of, any patent or other proprietary right. Nothing in this document should be construed as a warranty or guarantee by AAP, and the only applicable warranties will be those set forth in AAP acknowledgement or in any printed warranty documents issued by AAP. The foregoing may be waived or modified only in writing by an AAP officer.

For a complete technical overview of all Reynobond® products, visit [www.reynobond.com](http://www.reynobond.com).

### Disclaimer

Laws and building and safety codes governing the design and use of AAP's products, and specifically aluminum composite materials, vary widely. It is the responsibility of the owner, the architect, the general contractor, the installer and the fabricator/transformer, consistent with their roles, to determine the appropriate materials for a project in strict conformity to all applicable national, regional and local building codes and regulations. REYNOBOND IS COMBUSTIBLE; IT COULD CATCH FIRE AND BURN. SEE AAP WEBSITE FOR PRODUCT WARNINGS. ANY LABORATORY TESTING INFORMATION PROVIDED BY AAP APPLIES ONLY TO THE PARTICULAR PRODUCT OR ASSEMBLY TESTED AND DOES NOT NECESSARILY REPRESENT HOW PRODUCTS WILL ACTUALLY PERFORM IN USE.