

**REYNOBOND®**Technical  
Bulletin

# Engineering Properties

## U.S. and Metric Equivalent

### Technical Engineering Properties

Composite-designed Reynobond® material consist of a thermoplastic compound core faced with two sheets of aluminum. There are two varieties, a Polyethylene (PE) core and a Fire Resistant (FR) core.

PROPERTY		UNITS	RB12oPE- 3mm	RB16oFR - 4mm	RB24oFR - 6mm	Solid Al(1)
THICKNESS		in mm	0.118 3.0	0.157 4.0	0.236 4.0	0.197 5.0
WEIGHT		lb/ft <sup>2</sup> kg/m <sup>2</sup>	0.94 4.59	1.53 7.48	2.10 10.25	2.78 13.57
BOND INTEGRITY	MIN. BOND STRENGTH ASTM D1781	in-lb/in Nm/m	40 178	22.5 100	22.5 100	- -
	FLATWISE SHEAR ASTM D1002	lb/in <sup>2</sup> MPa	1.297 8.94	92.8 6.4	70.8 4.8	- -
ALLOWABLE BENDING STRESS		lb/in <sup>2</sup> MPa	11,500 79.3	11,500 79.3	11,500 79.3	11,500 79.3
COEFF. OF EXPANSION ASTM E228		in/in/°F mm/mm/°C	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>	1.31x10 <sup>-5</sup> 2.36x10 <sup>-5</sup>
STIFFNESS (EI) ASTM D393		lb-in <sup>2</sup> /in MPa-cm <sup>4</sup> /m	807 9.1x10 <sup>4</sup>	1,262 1.4x10 <sup>4</sup>	2,450 -	6,434 7.4x10 <sup>4</sup>
FLEXULAR MODULUS ASTM C393		lb/in <sup>2</sup> MPa	8.3x10 <sup>6</sup> 5.7x10 <sup>4</sup>	6.7x10 <sup>6</sup> 4.6x10 <sup>4</sup>	3.0x10 <sup>6</sup> 2.6x10 <sup>4</sup>	10x10 <sup>6</sup> 6.9 x10 <sup>4</sup>
MOMENT OF INERTIA		in <sup>4</sup> /in cm <sup>4</sup> /m	0.97x10 <sup>4</sup> 0.159	1.89x10 <sup>4</sup> 0.310	4.58x10 <sup>4</sup> 0.751	6.37x10 <sup>4</sup> 1.042
SECTION MODULUS		in <sup>3</sup> /in cm <sup>3</sup> /m	1.65x10 <sup>-3</sup> 1.065	2.41x10 <sup>-3</sup> 1.555	3.88x10 <sup>-3</sup> 2.503	6.47x10 <sup>-3</sup> 4.167
TENSIL YIELD		lb/in <sup>2</sup> MPa	8,300 57.23	6,367 43.90	6,010 41.44	19,000 130.0
FLATWISE TENSILE ASTM C297		lb/in <sup>2</sup> MPa	1,483 10.22	961 6.62	- -	- -
"R" THERMAL RESIST- ANCE		ft <sup>2</sup> hr°F/BTU m <sup>2</sup> K/w	0.034 6.0x10 <sup>-3</sup>	0.026 4.5x10 <sup>-3</sup>	0.04 7.0x10 <sup>-3</sup>	- -
MAXIMUM WIDTH		in mm	62 1,575	62 1,575	62 1,575	- -
MAXIMUM LENGTH		in mm	243 6.172	243 6.172	243 6.172	- -
SOUND TRANSMISSION COEFF. ASTM E90		-	- -	- -	- -	- -
FIRE PERFORMANCE		ASTM E84 ASTM D635	Class A CC1	Class A Untested	Class A Untested	- -

**ARCONIC**



# REYNOBOND®

Technical  
Bulletin

Information contained herein or related hereto is intended only for evaluation by technically skilled persons, with any use thereof to be at their independent discretion and risk. Such information is believed to be reliable, but Arconic Architectural Products LLC (“Arconic”) shall have no responsibility or liability for results obtained or damages resulting from such use. Arconic grants no license under, and shall have no responsibility or liability for infringement of, any patent or other proprietary right. Nothing in this document should be construed as a warranty or guarantee by Arconic, and the only applicable warranties will be those set forth in Arconic acknowledgement or in any printed warranty documents issued by Arconic. The foregoing may be waived or modified only in writing by an Arconic officer.

#### Disclaimer

Laws and building and safety codes governing the design and use of AAP’s products, and specifically aluminium composite materials, vary widely. It is the responsibility of the owner, the architect, the general contractor, the installer and the fabricator/transformer, consistent with their roles, to determine the appropriate materials for a project in strict conformity to all applicable national, regional and local building codes and regulations.



**ARCONIC**

©2018 Arconic Architectural Products LLC. Reynobond® and Reynolux® are registered trademarks of Arconic Inc.

ARCONIC ARCHITECTURAL PRODUCTS LLC

50 Industrial Boulevard  
Eastman, GA 31023-4129  
Tel. 800 841 7774  
[www.reynobond.com](http://www.reynobond.com)